

# Micron MC-900 Pt. 1

## ***Micro Crystalline Zinc Phosphate, Make-Up***

Micron MC-900 phosphate coating system is a lubrication grade process for steel. Provides extrusion and metal drawing aid. Typical coating weights of 600-1200 mg/ft<sup>2</sup>. Provides typically darker coatings than conventional products and a preferred denser sludge by-product for less dusting on coils and less waste volume.

Micron MC-900 process is a two-part system (make-up & replenisher) that provides a micro crystalline, tightly bonded coating on steel. A zero-iron operating system with a unique coating structure for better lubrication.

Micron MC-900 process is an advanced phosphate coating which includes a catalyst for improved coatings which assist lubrication whether you are using poly lube or soap.

## **Features & Benefits**

- Lowest use cost. No dump operating system.
- Can be used in coil coating, barrel slug processes, immersion or spray.
- Reduced sludging and scale build-up on equipment.
- Bonds lubricant coatings tighter and more uniform.
- Can be used with all conventional and advanced lubricant coatings.
- Provides wide coating range as required: 600-1200 mg/sq.ft.

## **Physical Data**

pH	1.0
Product Type	Liquid
Spec. Gravity	1.48
lbs./gal.	12.34
Foam, 0 = Low, 9 = High	0
Shelf-Life Years	10 years
Freeze Information	Not damaged by freezing.

## **Typical Processing**

1. Pre-clean as required with acid pickling and/or alkaline cleaning.
2. Rinse

3. Rinse
4. Phosphate coat: micron MC-900 or MC-900 (make-up & replenisher). Use 7%~ of make-up = 21 points total acid part #1 to prepare a new bath.
5. Rinse
6. Hot rinse, 150 F., 30-60 sec., neutralized to pH of 9~ (w/856-l)
7. Lubricant coat: loc-lube soap, poly-lube, lime, oil etc.

## Packaging

Container Type	Poly
Net Units	680
Tare Wt.	25 lb.
Gross Wt.	690
DOT_Name	UN 3264, Corrosive liquid, acidic, inorganic, N.O.S., (Phosphoric & Nitric Acids), 8, PG II.
DOT Hazard	Corrosive.
Tarriff ID	

## Use Parameters

Concentration Range	20-30 points total acid
Temperature Range	175 – 190 Deg. F.
Time Range	4 – 10 min.
Agitation	n/a

## Waste Disposal

Neutralize pH, remove fats, oils, grease, and heavy metals.

## Holding Tank Materials of Construction

Acid resistant, stainless, or poly.

## Other Information

It is important that the OSHA DATA, "Material Safety Data Sheet" be carefully read and reviewed with the users of this product. OSHA data is required to be posted in the work area by law.

**WARRANTY:** HUBBARD-HALL INC. IS NOT RESPONSIBLE FOR THE MISUSE, MISAPPLICATION, OR MISHANDLING OF THIS PRODUCT. SEE THE TERMS AND CONDITIONS OF SALE ON OUR WEBSITE FOR ADDITIONAL TERMS AND CONDITIONS



CONCERNING OUR PRODUCTS, INCLUDING BUT NOT LIMITED TO, LIMITATIONS AND DISCLAIMERS OF WARRANTIES AND LIABILITIES.

---

## Our People. Your Problem Solvers.

For more information on this process,  
please call us at 203.756.5521 or email: [techservice@hubbardhall.com](mailto:techservice@hubbardhall.com)

Hubbard-Hall holds certifications for **ISO 9001:2015**, Responsible Distribution, as accredited by the **ACD** (Alliance for Chemical Distributors) and as a **Women-Owned Small Business**, as well as maintaining an association with **Omni-Chem**<sup>136</sup>.