

Lube Coat MG-11

Manganese Phosphate, Non-Nickel

MG-11 is a nickel free manganese phosphate conversion coating for use on steel and cast iron. Provides a lubricant "break-in" surface coating that prevents metal to metal friction. Used on cams, cranks, gears, bolts, pinions, piston rings, military parts, etc.

MG-11 provides a permanent coating which is used for lubrication, anti-galling/friction and anticorrosion. Provides a tight grain coating with fine micro finish. Bath can provide 500 - 3,000 mg/ft² as needed.

The lower temperature process provides lower cost of operation, safer to employees using, less heat sludge and waste byproduct.

Meets or exceeds needs of various automotive, appliance, military, government and other specifications. MIL DTL-16232G Type M, Chrysler PS-1462, Ford M3P33 A2, GM 4277M, EN 12476.

Features & Benefits

- Ease of control and use.
- A single product which is highly versatile.
- Can be used on steel, cast iron, tool steels, powdered and sintered metal.
- Provides coating weights of 400-3000 mg/ft², as required by process.
- A wide level of coating weights can be obtained depending on requirements.
- Coating resists galling.
- MG-11 can be used with and without a pre-rinse grain refiner, depending on specifications required.

Physical Data

pH	1
Product Type	Liquid
Spec. Gravity	1.34
lbs./gal.	11.18
Foam, 0 = Low, 9 = High	0
Shelf-Life Years	10 years
Freeze Information	Not damaged by freezing.

Typical Processing

1. Alkaline pre-clean metal surface. Must be free of oils, smut.
2. Rinse
3. Acid descale, derust or desmut. (optional if needed)
4. Rinse (optional grain refiner rinse can be used see Toner MG)
5. MG-11 180-210 deg. F., 5-30 min., 6-18 pts, 8-15% b.v. Fe < 6.0
6. Rinse,
7. Rinse Neutralized (to a pH 8-10, Warm to hot.
8. Light anti-corrosion oil or optional final finish.
9. Loc-Lube #5, 6, NR-50 (soap coatings), Polymer Lube TL-48, wax, oil. Ideal operating bath is: total acid: 10-12, free acid 2.0-2.5, ratio 5-6, iron < 3.0, temp 190 + F.

Packaging

Container Type	Poly
Net Units	615
Tare Wt.	25 lb.
Gross Wt.	640
DOT_Name	UN 3264, Corrosive Liquid, Acidic, inorganic, N.O.S., (Phosphoric & Nitric Acids), 8, PG II.
DOT Hazard	Corrosive
Tariff ID	2835.29

Use Parameters

Concentration Range	8-15%, 6-18 points TA
Temperature Range	175 – 210 deg. F.
Time Range	5 – 30 minutes.
Agitation	n/a

Waste Disposal

Contain and treat for metals, acids

Holding Tank Materials of Construction

Acid resistant, stainless, or poly.



Other Information

It is important that the OSHA DATA, "Material Safety Data Sheet" be carefully read and reviewed with the users of this product. OSHA data is required to be posted in the work area by law.

WARRANTY: HUBBARD-HALL INC. IS NOT RESPONSIBLE FOR THE MISUSE, MISAPPLICATION, OR MISHANDLING OF THIS PRODUCT. SEE THE TERMS AND CONDITIONS OF SALE ON OUR WEBSITE FOR ADDITIONAL TERMS AND CONDITIONS CONCERNING OUR PRODUCTS, INCLUDING BUT NOT LIMITED TO, LIMITATIONS AND DISCLAIMERS OF WARRANTIES AND LIABILITIES.

Our People. Your Problem Solvers.

For more information on this process,
please call us at 203.756.5521 or email: techservice@hubbardhall.com

Hubbard-Hall holds certifications for **ISO 9001:2015**, Responsible Distribution, as accredited by the **ACD** (Alliance for Chemical Distributors) and as a **Women-Owned Small Business**, as well as maintaining an association with **Omni-Chem**¹³⁶.