

Neutral Salt HH

Neutral Salt HH is a chemically balanced mixture of chlorides formulated for a specific range of operating temperatures. All chemicals incorporated into the formulation are technical grade to insure high purity, high grade, trouble-free mixture.

Neutral Salt HH is used as a molten salt bath for a neutral heat transfer medium within its operating range of temperatures (1700-2400oF.) for the heat treatment of alloy steels requiring temperatures within the temperature range of Neutral Salt HH. It is also used for the heat treatment of high-speed steels requiring temperatures of 2100oF. Neutral Salt HH can be used up to 2400oF. but only for intermittent operation. For constant requirements, between 2100 to 2400oF., Neutral Salt HHS should be used.

Physical Data

Melting Point	1600 °F
Weight	165 lbs./cu. Ft
Operating Range:	1700-2400°F.

Chemical Control Required

Chemicals and chemical compounds should not be introduced into the Neutral HH salt bath such as nitrates, cyanides, oils, cleaning compounds, or other types of contaminants. These contaminants will not only change the neutrality of the salt bath, but ruin the Neutral HH salt bath, necessitating dumping the bath and making up a new one.

The Neutral HH molten salt bath is very stable, but the neutrality must be maintained by bubbling methyl chloride through the molten bath to control the alkalinity. Graphite rods must also be used to remove metallic oxides. Neutral HH Rectifier can be used if methyl chloride is not available. However, graphite rods should be used to remove the metallic oxides. It is also advisable to daily desludge the Neutral HH salt bath to aid in keeping the neutrality of the salt bath. There is a Chemical Control Bulletin available upon request.



Cleaning Requirements

Hot water is recommended for the removal of solidified Neutral Salt HH from the heat-treated work. After the salts have been removed in hot water, the remaining oil can be removed in a hot alkali cleaner.

Equipment Requirements

Electric immersed or submerged electrode type furnaces with ceramic pots are the best type of pot furnace for the Neutral HH salt bath.

WARRANTY: THE QUALITY OF THIS PRODUCT IS GUARANTEED ON SHIPMENT FROM OUR PLANT. IF THE USE RECOMMENDATIONS ARE FOLLOWED, DESIRED RESULTS WILL BE OBTAINED. SINCE THE USE OF OUR PRODUCTS IS BEYOND OUR CONTROL, NO GUARANTEE EXPRESSED OR IMPLIED IS MADE AS TO THE EFFECTS OF SUCH USE, OR THE RESULTS TO BE OBTAINED.

Our People. Your Problem Solvers.

For more information on this process,
please call us at 203.756.5521 or email: techservice@hubbardhall.com

Hubbard-Hall holds certifications for **ISO 9001:2015**, Responsible Distribution, as accredited by the **ACD** (Alliance for Chemical Distributors) and as a **Women-Owned Small Business**, as well as maintaining an association with **Omni-Chem**¹³⁶.