

Metal Guard® 820

Metal Guard 820 is a water-soluble alkaline liquid concentrate specifically formulated to provide temporary rust protection of steel indoors. It leaves a dry, invisible, non-oily film that will not hinder subsequent operations. Metal Guard 820 solutions can be used as a final dip in tumbling or soak operations to prevent possible oxidation of steel parts. Being a water solution, it does not present a fire hazard, nor does it present a toxicity problem.

Features & Benefits

Excellent short-term-in-process rust protection	Prevents rust on high value parts between process steps
Easily soluble in water	Easily removed with a mild alkaline cleaner
Used at low concentrations	Cost effective over large applications

Physical Data

Specific gravity	1.11
Vapor pressure	< 17.5 @ 20°C
Solubility in water	Infinite
Appearance and odor	Clear, red liquid

Operating Conditions

Metal Guard 820 is commonly used at 1% to 3% (volume) with water and at temperatures ranging from ambient to 180°F. Higher temperatures facilitate faster drying and speed up production, while higher concentrations provide greater protection against oxidation. Solution replenishment is non-hazardous, whether added to a hot or cold bath.

Equipment

Tanks may be made of mild steel, Polypropylene, or stainless steel with provision for heating the bath, if required. It is not necessary to exhaust the solution.



Titration Method

1. Measure a 100 mL sample into a 250 mL Erlenmeyer flask from a graduated cylinder.
2. Add 6 to 8 drops Bromocresol Purple indicator and mix.
3. Titrate with 0.5 N Hydrochloric Acid until the color changes from purple to yellow.
Note: Yellow color must persist for at least 30 seconds.
4. Record mL of used.

Calculation:

$$\text{Concentration} = \text{mL } 0.5 \text{ N HCl} \times 0.62$$

Test Kit Method

1. Measure a 25 mL sample using graduated cylinder. Pour sample into mixing bottle.
2. Add 5 drops Bromocresol Purple indicator and mix.
3. Add 0.72 N Hydrochloric Acid dropwise while mixing solution until the color changes from purple to yellow.
Note: Yellow color must persist for at least 30 seconds.
4. Record number of drops used.

Calculation:

$$\text{Concentration} = \# \text{ Drops } 0.72 \text{ N HCl} \times 0.17$$

Caution

Metal Guard 820 is a water solution of chemicals; thus, it does not present a fire hazard, however, it is an alkaline product and must be handled accordingly. Wear rubber gloves and chemical goggles when handling Metal Guard 820.

WARRANTY: HUBBARD-HALL INC. IS NOT RESPONSIBLE FOR THE MISUSE, MISAPPLICATION, OR MISHANDLING OF THIS PRODUCT. SEE THE TERMS AND CONDITIONS OF SALE ON OUR WEBSITE FOR ADDITIONAL TERMS AND CONDITIONS CONCERNING OUR PRODUCTS, INCLUDING BUT NOT LIMITED TO, LIMITATIONS AND DISCLAIMERS OF WARRANTIES AND LIABILITIES.



563 South Leonard Street, Waterbury, CT 06708 • HubbardHall.com • 800-648-3412

Product Bulletin

Product Name: Metal Guard® 820

Product Code: 2508020

Revision Date: June 2, 2025

Our People. Your Problem Solvers.

For more information on this process,
please call us at 203.756.5521 or email: techservice@hubbardhall.com

Hubbard-Hall holds certifications for **ISO 9001:2015**, Responsible Distribution, as accredited by the **ACD** (Alliance for Chemical Distributors) and as a **Women-Owned Small Business**, as well as maintaining an association with **Omni-Chem**¹³⁶.