

Halltronic R 629


Features & Benefits

High purity	Consistent performance; No side reactions
High concentration	Smaller storage footprint
Liquid	Ready to use; Less material handling

Operating Conditions

Sodium Chlorate Usage Data for Ferric Chloride Solutions

Chemical Reactions



Therefore: 1 mole of iron etched requires ½ mole of NaClO₃ and 3 moles of HCl for regeneration

1 mole of Fe = 55.847 grams

1 mole of NaClO₃ = 106.44 grams

1 mole HCl = 36.46 grams

1 pound of Iron = 454 grams = 8.13 moles and requires 4.06 moles (= 432.1 grams = 0.95 lb) NaClO₃ and 24.39 moles (= 889.3 grams = 1.96lb) HCl for regeneration.

Halltronic R 629 solution contains 629 grams/L NaClO₃ or 5.25 lb/Gal

Industrial grade HCl (Muriatic Acid) is 30% HCl and contains 344.7 g/l HCl or 2.87 lb/Gal.

Therefore: 1 pound of iron etched requires -

0.18 gallons of Halltronic R 629

and

0.68 gallons of Muriatic acid (30% HCl) for regeneration



Product Bulletin

Product Name: Halltronic R 629

Product Code: 2707017

Revision Date: May 28, 2025

The numbers given above are for an ideal reaction with 100% efficiency. Actual usage will probably be 10% to 20% higher depending on temperature, type of alloy, etc.

WARRANTY: HUBBARD-HALL INC. IS NOT RESPONSIBLE FOR THE MISUSE, MISAPPLICATION, OR MISHANDLING OF THIS PRODUCT. SEE THE TERMS AND CONDITIONS OF SALE ON OUR WEBSITE FOR ADDITIONAL TERMS AND CONDITIONS CONCERNING OUR PRODUCTS, INCLUDING BUT NOT LIMITED TO, LIMITATIONS AND DISCLAIMERS OF WARRANTIES AND LIABILITIES.

Our People. Your Problem Solvers.

For more information on this process,
please call us at 203.756.5521 or email: techservice@hubbardhall.com

Hubbard-Hall holds certifications for **ISO 9001:2015**, Responsible Distribution, as accredited by the **ACD** (Alliance for Chemical Distributors) and as a **Women-Owned Small Business**, as well as maintaining an association with **Omni-Chem**¹³⁶.