



Better Chemistry. **Better Business.**

Aquastrip THX

Product Code: 2572013
Revised Date: 8/9/2014

Aquastrip THX

DESCRIPTION

Aquastrip THX is a mildly acidic new generation thixotropic hydrogen peroxide activated paint stripper, used to remove tenacious polymeric coatings including epoxy paints from ferrous, non-ferrous and composite substrates. This unique formulation allows for superior wetting and adhesion to large vertical surfaces. **Aquastrip THX** is a safe and effective paint stripper that does not contain any hazardous solvents.

FEATURES AND BENEFITS

- Contains non-hazardous solvents
- No flash point
- Can be used on most metals
- Biodegradable
- Excellent adhesion properties for use on vertical surfaces
- 12 month shelf life

TYPICAL APPLICATIONS

- Excellent choice for removal of polyurethane and epoxy powder paints.
- Excellent for use on large equipment and surfaces.

APPLICATION INSTRUCTIONS

For best results apply **Aquastrip THX** with an airless spray system. An air operated chemical resistant piston pump should be used and the recommended application tip size should be between 0.53 and 0.79.

Aquastrip THX can also be applied by brush, but the bristles should be constructed of synthetic or poly materials.



Better Chemistry. **Better Business.**

Aquastrip THX

Product Code: 2572013
Revised Date: 8/9/2014

OPERATING INSTRUCTIONS

Spray an initial “tack” coat evenly across the surface of the part being stripped. Allow the **Aquastrip THX** to dwell for 30 minutes, reapply at 2-3 mils of thickness for every 1 mil of paint or powder to be removed. Allow the **Aquastrip THX** to dwell 4–10 hours. Rinse completely allowing the part surface to dry completely.

Temperature and air circulation (wind) can affect the paint stripping process. Optimal temperature range is 70° F to 80° F. High temperatures combined with wind or high air circulation will result in pre-mature evaporation and drying too early. Lower temperatures cause coatings to harden prohibiting performance and increasing dwell times. **Aquastrip THX** is designed to stay “wet” much longer than competitive products, often 12 to 16 hours. **Aquastrip THX** will continue to work as long as it appears “wet”. Visually inspect the part surface for the most optimal time to rinse with a high pressure spray wand.

CAUTION

Always read the Material Safety Data sheet before using this product. **Aquastrip THX** should always be used with adequate ventilation and proper safety equipment. Skin will bleach when it comes in contact with product. If skin exposure occurs, rinse with water for 10-15 minutes.

WARRANTY

THE QUALITY OF THIS PRODUCT IS GUARANTEED ON SHIPMENT FROM OUR PLANT. IF THE USE RECOMMENDATIONS ARE FOLLOWED, DESIRED RESULTS WILL BE OBTAINED. SINCE THE USE OF OUR PRODUCTS IS BEYOND OUR CONTROL, NO GUARANTEE EXPRESSED OR IMPLIED IS MADE AS TO THE EFFECTS OF SUCH USE, OR THE RESULTS TO BE OBTAINED.